





IEC61215(2021), IEC61730(2016) | ISO9001:2015: Quality Management System | ISO14001:2015: Environment Management System ISO45001:2018: Occupational health and safety management systems | IEC62941: 2019: Quality system for PV module manufacturing



High Power Output

SMBB technology reduces the distance between busbars and finger grid lines, improving reliability and increasing output



ZERO LID (Light Induced Degradation)

N-type solar cell has no LID naturally which can increase power generation



Higher Reliability

Adpoted Jolywood lastest J-TOPCon2.0 technology, No polysilicon wrap around, Full electrical isolation, Zero leakage current; Much Safer for roof



Jolywood Delivers Reliable Performance Over Time

- Leader of N-type bifacial manufacturer
- Full-automatic facility and industry-leading technology
- · Best-in-class durability and reliability
- BNEF Tier One



Better Weak Illumination Response

Higher power output even under low-light environments like on cloudy or foggy days



Better Temperature Coefficient


Higher power generation under working conditions, thanks to passivating contact cell technology



Lighter Module Weight

Reduces weight by more than 20% compared to bifacial double glass module

Linear Performance Warranty



Subject to the terms and conditions contained in the applicable Jolywood Solar Limited Warranty Statement. Also this 25 -year limited product warranty is available only for products installed and operating on residential rooftops in certain regions











Electrical Properties	STC*					
Testing Condition	Front Side					
Peak Power (Pmax) (W)	415	420	425	430	435	440
MPP Voltage (Vmp) (V)	31.7	31.9	32.1	32.3	32.5	32.7
MPP Current (Imp) (A)	13.10	13.17	13.24	13.32	13.39	13.46
Open Circuit Voltage (Voc) (V)	37.7	37.9	38.1	38.3	38.4	38.6
Short Circuit Current (Isc) (A)	13.91	13.98	14.05	14.12	14.18	14.25
Module Efficiency (%)	21.25	21.51	21.76	22.02	22.27	22.53

*STC: Irradiance 1000 W/m², Cell Temperature 25°C, AM1.5
The data above is for reference only and the actual data is in accordance with the pratical testing Power Measurement Tolerance ±3%

Electrical Properties	NOCT*					
Testing Condition	Front Side					
Peak Power (Pmax) (W)	315	318	322	326	330	334
MPP Voltage (Vmp) (V)	29.8	30.0	30.2	30.3	30.5	30.7
MPP Current (Imp) (A)	10.56	10.62	10.67	10.74	10.82	10.88
Open Circuit Voltage (Voc) (V)	36.0	36.2	36.4	36.6	36.8	37.0
Short Circuit Current (Isc) (A)	11.22	11.27	11.33	11.38	11.44	11.49

*NOCT: Irradiance 800 W/m², Ambient Temperature 20°C, Wind Speed 1 m/s

Operating Properties Operating Temperature (°C) -40°C~+85°C Maximum System Voltage (V) 1500V DC (IEC) Maximum Series Fuse Rating (A) 30 Power Tolerance 0~+5W Front Static Load Snow load 5400Pa, Wind load 2400Pa

Temperature Coefficient		
Temperature Coefficient of Pmax*	-0.300%/°C	
Temperature Coefficient of Voc	-0.250%/°C	
Temperature Coefficient of Isc	+0.045%/°C	
Nominal Operating Cell Temperature (NOCT)	42±2℃	

^{*}Temperature Coefficient of Pmax±0.03%/°C


Mechanical Properties	
Cell Size	182.00mm*91.00mm
Number of Cells	108pcs(12*9)
Module Dimension	1722mm*1134mm*30mm
Weight	21.5kg
Front Glass*	3.2mm
Frame	Anodized Aluminium Alloy
Junction Box	IP68 (3 diodes)
Length of Cable	4.0mm², +300mm/-180mm (Cable length can be customized)

*Fully strengthened glass


NOTE:

JOLYWOOD (TAIZHOU) SOLAR

Engineering Drawing (unit: mm)



Characteristic Curves | HT108N-420



Packaging Configuration					
Packing Type	20'GP	40'GP	40'HQ		
Piece/Pallet		36			
Pallet/Container	6	13	26		
Piece/Container	216	468	936		

"The specification and key features described in this datasheet may deviate slightly and are not guaranteed. Due to ongoing innovation, R&D enhancement, jolywood (Taizhou) Solar Technology Co., Ltd. reserves the right to make any adjustment to the information described herein a any time without notice. Please always obtain the most recent version of the datasheet of the control of the datasheet of



TECHNOLOGY CO.,LTD. Zone,Taizhou, Jiangsu Province, China, 225500 www.jolywood.cn TEL: +86 523 80612799 Email: mkt@jolywood.cn

